3M Scotch-Weld[™] Industrial Adhesive 4475

Technical Data December, 2007

Features

- Dries quickly to a firm bond.
- Excellent resistance to water, plasticizer migration, many detergent and soap solutions, oils and grease.
- A general purpose adhesive for bonding most vinyls, ceramics, glass, leather and cloth to a variety of substrates.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Viscosity	6,500 - 10,500	
Brookfield Viscometer	RVF #5 sp. @ 20 rpm @ 80°F	
Solids Content (approx.)	41-45% (by wt.)	
Base	Synthetic Resin	
Color	Clear	
Net Weight	8.3 lbs./gal.	
Flash Point	20°F CC	
Coverage	487 sq. ft. per gallon (1 Mil Dry Film)	
Solvent	methyl ethyl ketone (MEK)	

3M[™] Scotch-Weld[™] Industrial Adhesive 4475

Application Equipment Suggestions

Note: Appropriate application equipment can enhance adhesive performance. The user is responsible for evaluating application equipment in light of the user's particular purpose and method of application.

1. Pumping

5-Gallon Pail Dispensing System

Pump -9:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, $4^{1}/4^{1}$ diameter air motor minimum.

Pail cover to be used to reduce solvent loss.

55-Gallon Drum Dispensing System

Pump - 10:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, $4^{1}/4^{11}$ diameter air motor minimum, Bung mount type.

2. Accessories

Hose – 1000 psi minimum working pressure, nylon lined. Flow rate at 40°F, 20 ft. of ³/₄-ID plus 10 ft. ¹/₂-ID and a flow gun equals 1 pound/minute at pump air pressure of 75 psi.

3. Chemical Resistance Requirements

Synthetic materials in contact with this product must be resistant to ketones and aromatic solvents. Compare, nylon or Teflon[®] coatings are suggested for packings and gaskets.

Handling/Application Information

Directions for Use

- 1. Surface Preparation: Best results are achieved on clean, dry surfaces. Oil, grease and other contaminants can be removed by wiping with a solvent such as methyl ethyl ketone (MEK).*
- **2. Application:** Apply adhesive to one or both surfaces (best results are obtained by coating both surfaces) and bond immediately using firm pressure.
- **3. Drying Time:** Allow to dry a minimum of 24 hours for maximum strength.
- **4.** Cleanup: Remove unhardened or hardened material with cloth dampened with a solvent such as methyl ethyl ketone (MEK).*

*Note: When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

3M[™] Scotch-Weld[™] Industrial Adhesive 4475

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

180° Peel Strength – Canvas/Steel			
Time @ 75°F	Test Temp.	Value (Ibs./in. width)	
1 day	75°F	13	
3 days	75°F	24	
5 days	75°F	27.5	
7 days	75°F	32.5	
2 wk.	75°F	35	
3 wk.	75°F	44	
after 3 wk.	-30°F	22	
after 3 wk.	150°F	17	
after 3 wk.	180°F	7	

Storage

Best storage temperature is 60-80°F (16-27°C). Higher temperatures reduce normal storage life. Lower temperatures cause increased viscosity of a temporary nature. Rotate stock on a "first in, first out" basis.

Shelf Life

When stored at the recommended temperature in the original, unopened container, this product has a shelf life of 15 months.

3M[™] Scotch-Weld[™] Industrial Adhesive 4475

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer 3M and Scotch-Weld are trademarks of 3M Company.
Teflon is a registered trademark of E.I. DuPont de Nemours Co.
Printed in U.S.A.
©3M 2007 78-6900-0247-8 (12/07)